



# TECHNICAL SPECIFICATION - CORE BOARD

(Grade: 200 X)

SN	PROPERTY	UNIT	Grammages									
			150±3%	200±3%	250±5%	300±5%	350±5%	400±5%	450±5%	500±5%	550±5%	600±5%
1	Grammage	gm/m2	150±3%	200±3%	250±5%	300±5%	350±5%	400±5%	450±5%	500±5%	550±5%	600±5%
2	Bulk	cc/g	1.50-1.70	1.50-1.70	1.50-1.70	1.50-1.70	1.50-1.70	1.50-1.70	1.50-1.70	1.50-1.70	1.50-1.70	1.50-1.70
3	Burst Strength, min.	kPa	350	400	450	500	550	600	620	650	670	700
4	Ply Bond , min.	J/M2	200	200	200	200	200	200	200	200	200	200
5	COBB	GSM	50 - 150 ( INDICATIVE )									
6	Moisture	%	7±1	7±1	7±1	7±1	7±1	7±1	7±1	7±1	7±1	7±1

<b>Test Condition:</b>  RH = 50%±2%  Temp = 23±1°C	<u>All reels with core plug fitted, stretch film wrapped.</u>  <u>Core dia 76 mm unless specified</u>	<i>Test Method</i>  <i>TAPPI Standard</i>
--	---	---

Quality Control  
 Middle East Paper Company  
 Jeddah. KSA