



MIDDLE EAST PAPER COMPANY

QSP/FG-01

QUALITY SPECIFICATIONS

Rev. No.: 00

TEST LINER

Date: 15 June 2008

PHYSICAL CHARACTERISTICS																	
PARAMETERS	UNIT		GRAMMAGE														REMARKS FOR NORMS
			TL 95	TL 110	TL 112	TL 125	TL 127	TL 140	TL 145	TL 150	TL 160	TL 175	TL 185	TL 190	TL 200	TL 210	
Substance	GSM	Target	95	110	112	125	127	140	145	150	160	175	185	190	200	210	± 5%
Bursting Strength	KPa	MIN	235	280	280	310	310	355	370	380	390	400	430	450	470	490	Controlled
RCT - CD	kN/m	MIN	0.80	1.00	1.00	1.10	1.10	1.40	1.45	1.50	1.70	2.00	2.10	2.15	2.20	2.30	Controlled
SCT - CD	kN/m	-	2.00	2.20	2.20	2.50	2.50	2.75	2.88	3.00	3.20	3.50	3.70	3.80	4.00	4.20	Indicative
Roughness (Bendtsen)	ml/min	TOP	1000 - 1500								1500 - 1800	1800 - 2000					Controlled
		BOT	1300 - 1700								1800 - 2000	2000 - 2300					Controlled
COBB ₆₀	gm/m ²	Range	50 - 70														Indicative
Moisture	%	Range	7 - 9														Controlled

*Testing Condition: Temperature = 23 ± 1°C; Relative Humidity = 50 ± 2% * Test Method = TAPPI

PRODUCT INFORMATION	
Reel Width, Preferably Trimmings	As specified
Reel Diameters,	As specified
Core Inside Diameter	101.4 – 101.6 mm
Packing	Stretch File Wrapped
Quantity Tolerance	As specified
STORAGE RECOMMENDATION	
Paper should be stored in a cool & dry place which is covered and ventilated. Should not be stored near any flammable material.	